

TABLE-3

Unit	Construction	Transmittance (%)	Reflectance (%)
A	Resin Plate-Air Layer-Glass Plate	82.97	14.31
B	AR Layer-Resin Plate-Air Layer-Glass Plate	85.76	11.17
C	Resin Plate-Transparent Sheet-Glass Plate	86.51	7.64
D	AR Layer-Resin Plate-Transparent Sheet-Glass Plate	95.75	4.01
E	AR Layer-Resin Plate-AR Layer-Air Layer-AR Layer-Glass Plate	92.12	4.33